

测试报告

编号 : GZIN1908041749MR_CN

日期 : 2019-09-27

页码 : 1 of 5



客户名称: 江苏万源新材料股份有限公司
客户地址: 镇江市丹徒区上党镇薛村工业园兴业路

样品名称 : 金色环氧铝箔

以上信息及样品由客户提供及确认, SGS 不承担证实客户提供信息的准确性、适当性和(或)完整性的责任。

SGS 参考号 : SHIN1908055523MR; 14743877

收样日期 : 2019-08-07

测试开始时间 : 2019-08-07

测试结束时间 : 2019-09-27

测试结果 : 请见下页 (除另有特别说明外, 此报告结果仅对测试样品负责)

通标标准技术服务有限公司广州分公司
检测中心
授权签名

谭红香

授权签字人



测试报告

编号 : GZIN1908041749MR_CN

日期 : 2019-09-27


页码 : 2 of 5

结果总结:

序号	测试项目	测试方法	结果	结论
1	酸性盐雾 (AASS) 试验	ASTM G85-11 附录 A1	外观等级: 10	/

备注: 合格: 达到要求
不合格: 未达到要求
/: 不下判定

原样照片:



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC 检测技术有限公司 广州分公司
Guangzhou Branch Testing Center Reliability Laboratory

198 Kazhu Road, Sciencetech Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t(86-20) 82155555 f(86-20) 82075188 www.sgs.com.cn
中国·广州·经济技术开发区科学城科珠路198号 邮编:510663 t(86-20) 82155555 f(86-20) 82075188 e sgs.china@sgs.com

测试报告

编号 : GZIN1908041749MR_CN

日期 : 2019-09-27

页码 : 3 of 5

测试项目: 酸性盐雾(AASS) 试验

样品描述: 金属片

测试方法: ASTM G85-11 附录 A1

测试条件:

沉降盐液浓度: (5±1)%NaCl (m/m)

试验箱温度: (35±2)°C

盐雾沉降率: (1.0~2.0)ml/(80cm²·h)

沉降盐液 pH 值 (25°C): 3.1~3.3

暴露时间: 1000 小时

测试结果:

样品		外观等级	综合等级
A	#1	10	10
	#2	10	
	#3	10	



测试报告

编号 : GZIN1908041749MR_CN

日期 : 2019-09-27

页码 : 4 of 5

备注:

1.评价面为非迎雾面

2.外观等级参照 EN ISO 10289: 2001, 按破坏面积评定:

破坏面积 A(%)	外观等级
0(无破坏)	10
$0 < A \leq 0.1$	9
$0.1 < A \leq 0.25$	8
$0.25 < A \leq 0.5$	7
$0.5 < A \leq 1.0$	6
$1.0 < A \leq 2.5$	5
$2.5 < A \leq 5.0$	4
$5.0 < A \leq 10$	3
$10 < A \leq 25$	2
$25 < A \leq 50$	1
$50 < A$	0




测试报告

编号 : GZIN1908041749MR_CN

日期 : 2019-09-27

页码 : 5 of 5

测试照片:



设备信息:

设备	型号	设备编号	校准日期	下次校准日期
盐水喷雾试验机	TG-2100-M	GZMR-AG-E123	2019-04-16	2020-04-15

附录信息:

此测试报告是报告编号 GZIN1908041749MR 的中文译本, 中英文版本如有歧义, 概以英文版为准。

***** 报告结束*****



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
 Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

198 Kazhu Road, Science Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t (86-20) 82155555 f (86-20) 82075188 www.sgs.com.cn
 中国·广州·经济技术开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075188 e sgs.china@sgs.com